

# BE 15 EPOXY

MIXING RATIO BY WEIGHT

100:28

READY MIX, Kg	PART A, Kg	PART B, Kg
1	0,78	0,22
2	1,56	0,44
3	2,34	0,66
4	3,12	0,88
5	3,90	1,10
6	4,68	1,32
7	5,46	1,54
8	6,24	1,76
9	7,02	1,98
10	7,80	2,20
11	8,58	2,42
12	9,36	2,64
13	10,14	2,86
14	10,92	3,08
15	11,70	3,30
16	12,48	3,52
17	13,26	3,74
18	14,04	3,96
19	14,82	4,18
20	15,60	4,40

# BE 30 EPOXY

MIXING RATIO BY WEIGHT

100:25

READY MIX, Kg	PART A, Kg	PART B, Kg
1	0,80	0,20
2	1,60	0,40
3	2,40	0,60
4	3,20	0,80
5	4,00	1,00
6	4,80	1,20
7	5,60	1,40
8	6,40	1,60
9	7,20	1,80
10	8,00	2,00
11	8,80	2,20
12	9,60	2,40
13	10,40	2,60
14	11,20	2,80
15	12,00	3,00
16	12,80	3,20
17	13,60	3,40
18	14,40	3,60
19	15,20	3,80
20	16,00	4,00

# BE 60 EPOXY

MIXING RATIO BY WEIGHT

100:25

READY MIX, Kg	PART A, Kg	PART B, Kg
1	0,80	0,20
2	1,60	0,40
3	2,40	0,60
4	3,20	0,80
5	4,00	1,00
6	4,80	1,20
7	5,60	1,40
8	6,40	1,60
9	7,20	1,80
10	8,00	2,00
11	8,80	2,20
12	9,60	2,40
13	10,40	2,60
14	11,20	2,80
15	12,00	3,00
16	12,80	3,20
17	13,60	3,40
18	14,40	3,60
19	15,20	3,80
20	16,00	4,00

# BE 180 EPOXY

MIXING RATIO BY WEIGHT

100:25

READY MIX, Kg	PART A, Kg	PART B, Kg
1	0,80	0,20
2	1,60	0,40
3	2,40	0,60
4	3,20	0,80
5	4,00	1,00
6	4,80	1,20
7	5,60	1,40
8	6,40	1,60
9	7,20	1,80
10	8,00	2,00
11	8,80	2,20
12	9,60	2,40
13	10,40	2,60
14	11,20	2,80
15	12,00	3,00
16	12,80	3,20
17	13,60	3,40
18	14,40	3,60
19	15,20	3,80
20	16,00	4,00